



Chemicals Plus, LLC
Miami - USA
info@chemicals-plus.com
www.chemicals-plus.com
+1 786-838-1826

Polyethylene FT3200

Description

FT3200 is a Low Density Polyethylene for Film Extrusion. Tubular Technology. Unmodified.

CAS-No. 9002-88-4

Applications

FT3200 is recommended for:

Heavy-duty bags
Shrink film

Construction films
Agricultural films

Additives

FT3200 contains no additives.

Special Features

FT3200 is optimised to deliver:

Excellent shrink performance

Physical Properties

Property	Typical Value Test Method	
	Data should not be used for specification work	
Density	920 kg/m³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	0,25 g/10min	ISO 1133
Melting temperature (DSC)	110 °C	ISO 11357-3
Vicat softening temperature A,	92 °C	ISO 306

Film Properties

Film properties are measured on 125 µm sample produced on a 60 mm W&H extruder with IBC cooling at BUR = 1:2,5.
MD = machine direction, TD = transverse direction.

Property	Typical Value	Test Method
Data should not be used for specification work		
Dart Drop	500 g	ISO 7765-1
Tensile Strain at Break	MD 400 %	ISO 527-3
Tensile Strain at Break	TD 600 %	ISO 527-3
Tensile Strength	MD 25 MPa	ISO 527-3
Tensile Strength	TD 26 MPa	ISO 527-3
Tensile Modulus ₁	MD 160 MPa	ASTM D 882-A
Tensile Modulus	TD 160 MPa	ASTM D 882-A



Chemicals Plus, LLC
Miami - USA
info@chemicals-plus.com
www.chemicals-plus.com
+1 786-838-1826

Polyethylene FT3200

Tear resistance (Elmendorf)	MD 4N	ISO 6383/2
	TD 7N	
Coefficient of friction (Dynamic)	0,7	ISO 8295

1 MD = machine direction, TD = transverse direction.

Storage

FT3200 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Chemicals Plus representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

General statement on compliance to food contact regulations



Chemicals Plus, LLC
Miami - USA
info@chemicals-plus.com
www.chemicals-plus.com
+1 786-838-1826



Polyethylene FT3200

DISCLAIMER

To the best of our knowledge, the information contained in this document is accurate and reliable as of the date of publication; However, we assume no responsibility for the accuracy and completeness of such information.

Chemicals Plus makes no warranties that extend beyond the description contained herein. Nothing contained herein shall constitute a warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products to ensure the suitability of the products for the customer's particular purpose. The customer is responsible for the proper, safe and legal use, processing and handling of our products.

No liability will be accepted in respect of the use of Chemicals Plus products in conjunction with other materials.

The information contained in this document relates exclusively to our products when not used in conjunction with third party materials.